

BREEDONFloorX® is specifically designed to provide the specifier and contractors with a cost-effective domestic flooring concrete that has excellent easy-to-place and finish properties when compared to standard domestic flooring concretes.

It offers a great alternative to labour intensive industry standard concretes (BS8500-1 Table A14) as well as higher specification and bespoke self-compacting concrete products.

BREEDONFloorX® is produced with a characteristic strength of: C28/35 N/mm² and consistence: SF2.

BREEDONFloorX® is supplied with fibres as standard which may eliminate the need for steel mesh. Where steel fibre addition is included this is at the approved dosage rate to ensure full compliance with NHBC requirements.

Where specifically requested BREEDONFloorX® can be supplied without fibres.

BREEDONFloorX® special admixtures and composition ensure that workability retention is maintained during the discharge and finishing processes. This allows the required finish* to be easily achieved with minimal labour involvement.

BREEDONFloorX® standard composition and formulation promotes an enhanced finish whilst reducing issues with cracking*.

BREEDONFloorX® is available at most of our production units and requires minimal lead time.

**Please be aware that good quality finished floors can only be achieved where good site practice and curing is maintained.*

TECHNICAL DATA

Strength:	35N/mm ²
Consistence:	SF2
Contains micro and steel fibres as standard	

BREEDONFloorX® is a high-quality concrete product, which has been formulated, produced, transported and supplied in accordance with our ISO 9001 third party accredited quality scheme (BSI) and in accordance with the relevant parts of BS8500 Part 2 and BS EN206.



The information given in this technical datasheet is based on our current knowledge and is intended to provide general notes on our products and their uses. Breedon Group plc endeavours to ensure that the information given is accurate but accept no liability for its use or its suitability for a particular application because of the product being used by the third party without our supervision.

Breedon Group Head Office:
Pinnacle House, Breedon Quarry,
Breedon on the Hill, Derby DE73 8AP

TO DISCUSS YOUR PROJECT REQUIREMENTS, AND FOR MORE INFORMATION ABOUT OUR PRODUCTS CONTACT:
01382 537600 (Scotland)
01332 694010 (England/Wales)
enquiries.breedon@breedongroup.com
www.breedongroup.com